

APLOMB ARCH MOSAIC CANVAS (M) *Ceramic*



PART NUMBER	PROFILE	AVAILABILITY
CR2687-ARCH00	MOSAIC	IN STOCK
GROUT JOINT	DIMENSIONS	THICKNESS
1/16"	12.6" x 12.6" = 1.10 sqft	5/16"
ORIGIN		
Italy		

NOTES

Due to the inherent characteristics of ceramic, there may be variations in color, movement and texture from lot to lot.

APPLICATION AREA

WALL	FLOOR	EXTERIOR	STEAM SHOWER	WET AREA	POOL	BACKSPLASH	FIREPLACE SURROUND	INTERIOR
Yes	No	No	Yes	Yes	No	Yes	Yes	Yes

The performance of surface covering products often depends on installation, environmental, and usage factors unique to each project. AKDO is not responsible for any effects that may be caused to products due to installation, wear from use, or exposure to environmental factors including but not limited to: hard water, chemicals, heat, flame, smoke, dirt or other substances. It is your responsibility to assess the project to determine if the product you are selecting is appropriate considering the unique characteristics of your installation, and to apply appropriate, high quality sealers when necessary. Please consult your installer for more information.

TECHNICAL DATA

FEATURES & STANDARD	SPECIFICATION	FEATURES & STANDARD	SPECIFICATION
Bond Strength - EN 1348	≥1.0 N/mm2 (Class C2 - EN 12004)	Breaking Strength - ISO 10545-4	S ≥600 N
Coefficient of Thermal Linear Expansion - ISO 10545-8	≤7MK-1	Crazing Resistance - ISO 10545-11	Resistant
Bending Resistance - ISO 10545-4	R ≥15 N/mm2	Moisture Expansion - ISO 10545-10	≤0.06% (0.6mm/m)
Reaction to Fire - N/A	A1	Regularity of Length & Width - ISO 10545-2	Compliant
Regularity of Rectangularity - ISO 10545-2	Compliant	Regularity of Straightness of Sides - ISO 10545-2	Compliant
Regularity of Thickness - ISO 10545-2	Compliant	Release of Dangerous Substances: ISO 10545-15	≤0.01mg/dm2 Cd ≤0.1mg/dm2 Pb
Resistance to Household Chemicals - ISO 10545-13	A	Resistance To Staining - ISO 10545-14	5
Resistance to Swimming Pool Salts - ISO 10545-13	A	Surface Flatness - ISO 10545-2	Compliant
Thermal Shock Resistance - ISO 10545-9	Resistant	Water Absorption - ISO 10545-3	10%<EV≤20%