

ELITE 12" X 24" DARK BROWN (N) *Porcelain*



PART NUMBER
PO2680-1224N0

PROFILE
MOSAIC

AVAILABILITY
IN STOCK

GROUT JOINT
1/16"

DIMENSIONS
11.81" x 23.62" = 1.937 sqft

THICKNESS
10mm

ORIGIN
Italy

NOTES
Available nationwide.

Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

APPLICATION AREA

| WALL | FLOOR | TRAFFIC | EXTERIOR | STEAM SHOWER | WET AREA | POOL | BACKSPLASH | FIREPLACE SURROUND |
|------|-------|---------------------|----------|-----------------|-------------|------|------------|-----------------------|
| Yes | Yes | Heavy Commercial | Yes | Yes | Yes | Yes | Yes | Yes |

INTERIOR

Yes

TECHNICAL DATA

| FEATURES & STANDARD | SPECIFICATION | FEATURES & STANDARD | SPECIFICATION |
|---|---|--|------------------------|
| Abrasion Resistance - ISO 10545-6 | ≤ 175mm ³ | Barefoot Ramp Test - DIN 51097 | A+B |
| Bond Strength - EN 1348 | ≥ 1.0 N/mm ² (Class C2 - EN 12004) | Breaking Strength - ISO 10545-4 | S ≥ 1300 N |
| Coefficient of Thermal Linear Expansion - ISO 10545-8 | ≤ 7MK-1 | Coefficient of Friction - B.C.R.A. Rep. CEC/81 | > 0.42 Dry, > 0.42 Wet |
| Impact Resistance - ISO 10545-5 | ≥ 0.55 | Bending Resistance - ISO 10545-4 | ≥ 1300 N |
| Moisture Expansion - ISO 10545-10 | ≤ 0.01% (0.1mm/m) | Reaction to Fire - N/A | A1 - A1fl |
| Regularity of Length & Width - ISO 10545-2 | Compliant | Regularity of Rectangularity - ISO 10545-2 | Compliant |
| Regularity of Straightness of Sides - ISO 10545-2 | Compliant | Regularity of Thickness - ISO 10545-2 | Compliant |
| Resistance to Household Chemicals - ISO 10545-13 | A | Resistance to Swimming Pool Salts - ISO 10545-13 | A |
| Booted Ramp Test - DIN 51130 | R9 NATURAL | Surface Flatness - ISO 10545-2 | Compliant |
| Water Absorption - ASTM C373 | ≤ 0.5% | Water Absorption - ISO 10545-3 | ≤ 0.1% |
| Pendulum Friction Test - AS/NZS 4586 | Class P3 | Pendulum Friction Test - UNE-ENV 12633 (CEN/TS 16165, Annex C) | Class C2 |
| Pendulum Friction Test - BS 7976-2002 (CEN/TS 16165, Annex C) | ≥ 36Dry, ≥ 36Wet | | |

TECHNICAL DATA

| FEATURES & STANDARD | SPECIFICATION |
|---------------------|---------------|
| DCOF - ANSI A.137.1 | > 0.42 Wet |