
AKDO

# ELITE 3-3/4'' X 21-1/4'' CHEVRON DARK BROWN (G) *Porcelain*



PART NUMBER
PO2680-CHEVG0

PROFILE
TILE

AVAILABILITY
REGULAR STOCK

GROUT JOINT
1/16"

DIMENSIONS
3.74" x 21.26" = 0.552 sqft

THICKNESS
10mm

ORIGIN
Italy

NOTES
Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

## APPLICATION AREA

| WALL | FLOOR | TRAFFIC | EXTERIOR | STEAM SHOWER | WET AREA | POOL | BACKSPLASH | FIREPLACE SURROUND |
|---|---|---|---|---|---|---|---|---|
| Yes | Yes | Commercial | Yes | Yes | Yes | Yes | Yes | Yes |

| INTERIOR |
|---|
| Yes |

## TECHNICAL DATA

| FEATURES & STANDARD | SPECIFICATION | FEATURES & STANDARD | SPECIFICATION |
|---|---|---|---|
| Abrasion Resistance - ISO 10545-6 | ≤ 175mm3 | Barefoot Ramp Test - DIN 51097 | A+B |
| Bond Strength - EN 1348 | ≥1.0 N/mm2 (Class C2 - EN 12004) | Breaking Strength - ISO 10545-4 | S ≥1300 N |
| Coefficient of Thermal Linear Expansion - ISO 10545-8 | ≤7MK-1 | Coefficient of Friction - B.C.R.A. Rep. CEC/81 | >0.42 Dry, >0.42 Wet |
| Frost Resistance - ASTM C1026 | Resistant | Impact Resistance - ISO 10545-5 | ≥0.55 |
| Bending Resistance - ISO 10545-4 | ≥ 1300 N | Moisture Expansion - ISO 10545-10 | ≤0.01% (0.1mm/m) |
| Reaction to Fire - N/A | A1 - A1fl | Regularity of Length & Width - ISO 10545-2 | Compliant |
| Regularity of Rectangularity - ISO 10545-2 | Compliant | Regularity of Straightness of Sides - ISO 10545-2 | Compliant |
| Regularity of Thickness - ISO 10545-2 | Compliant | Resistance to Household Chemicals - ISO 10545-13 | A |
| Resistance to Swimming Pool Salts - ISO 10545-13 | A | Booted Ramp Test - DIN 51130 | R9 NATURAL |
| Surface Flatness - ISO 10545-2 | Compliant | Thermal Shock Resistance - ISO 10545-9 | Resistant |
| Water Absorption - ASTM C373 | ≤0.5% | Water Absorption - ISO 10545-3 | ≤0.1% |
| Pendulum Friction Test - AS/NZS 4586 | Class P3 | Pendulum Friction Test - UNE-ENV 12633 (CEN/TS 16165, Annex C) | Class C2 |
| Pendulum Friction Test - BS 7976-2002 (CEN/TS 16165, Annex C) | ≥36Dry, ≥36Wet | | |
| DCOF - ANSI A.137.1 | > 0.42 Wet | | |