

RENAISSANCE 24" X 24" NEBBIA BIANCA (M) *Porcelain*



PART NUMBER	PROFILE	AVAILABILITY
PO2322-2424M0	TILE	IN STOCK
GROUT JOINT	DIMENSIONS	THICKNESS
1/16"	23.64" x 23.64" = 3.875 sqft	10mm
ORIGIN		
Italy		

NOTES

Available nationwide.

Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

APPLICATION AREA

WALL	FLOOR	TRAFFIC	EXTERIOR	STEAM SHOWER	WET AREA	POOL	BACKSPLASH	FIREPLACE SURROUND
Yes	Yes	Heavy Commercial	Yes	Yes	Yes	Yes	Yes	Yes
INTERIOR								
Yes								

The performance of surface covering products often depends on installation, environmental, and usage factors unique to each project. AKDO is not responsible for any effects that may be caused to products due to installation, wear from use, or exposure to environmental factors including but not limited to: hard water, chemicals, heat, flame, smoke, dirt or other substances. It is your responsibility to assess the project to determine if the product you are selecting is appropriate considering the unique characteristics of your installation, and to apply appropriate, high quality sealers when necessary. Please consult your installer for more information.

TECHNICAL DATA

FEATURES & STANDARD	SPECIFICATION	FEATURES & STANDARD	SPECIFICATION
Abrasion Resistance - ISO 10545-7	Cl. 4	Breaking Strength - ISO 10545-4	Average Value 3200 N
Crazing Resistance - ISO 10545-11	Resistant	Frost Resistance - ISO 10545-12	Resistant
Bending Resistance - ISO 10545-4	Average Value 50 N/mm2	Regularity of Length & Width - ISO 10545-2	± 0,15%
Regularity of Rectangularity - ISO 10545-2	± 0,2%	Regularity of Straightness of Sides - ISO 10545-2	± 0,1%
Regularity of Thickness - ISO 10545-2	± 5%	Surface Quality - ISO 10545-2	Compliant
Resistance To Staining - ISO 10545-14	Cl. 5	Resistance to Swimming Pool Salts - ISO 10545-13	GA
Surface Flatness - ISO 10545-2	± 0,35%	Thermal Shock Resistance - ISO 10545-9	Resistant
Water Absorption - ISO 10545-3	Average Value 0,08%	TECHNICAL DATA	
FEATURES & STANDARD	SPECIFICATION		
DCOF - ANSI A.137.1	> 0,42 wet		