


## RENAISSANCE 2" X 2" NEBBIA BIANCA (P) Porcelain



PART NUMBER
PO2322-M002P0

PROFILE MOSAIC AVAILABILITY
IN STOCK

GROUT JOINT

DIMENSIONS

THICKNESS

1/16"

11.81'' × 11.81'' = .97 sqft

10mm

ORIGIN

Italy

NOTES

Available nationwide.

Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

## APPLICATION AREA

WALL	FLOOR	TRAFFIC	EXTERIOR	STEAM SHOWER	WET AREA	POOL
Yes	Residential Floor Use Only	Residential	Yes	Wall Only	Wall Only	Yes
BACKSPI	LASH FIREPLA SURRO		<u> </u>			
Yes	Yes	Yes				

The performance of surface covering products often depends on installation, environmental, and usage factors unique to each project. AKDO is not responsible for any effects that may be caused to products due to installation, wear from use, or exposure to environmental factors including but not limited to: hard water, chemicals, heat, flame, smoke, dirt or other substances. It is your responsibility to assess the project to determine if the product you are selecting is appropriate considering the unique characteristics of your installation, and to apply appropriate, high quality sealers when necessary. Please consult your installer for more information.

## TECHNICAL DATA

FEATURES & STANDARD	SPECIFICATION	FEATURES & STANDARD	SPECIFICATION	
Abrasion Resistance - ISO 10545-7	Cl. 4	Breaking Strength - ISO 10545-4	Average Value 3200 N	
Crazing Resistance - ISO 10545-11	Resistant	Frost Resistance - ISO 10545-12	Resistant	
Bending Resistance - ISO 10545-4	Average Value 50 N/mm2	Regularity of Length & Width - ISO 10545-2	± 0,15%	
Regularity of Rectangularity - ISO 10545-2	± 0,2%	Regularity of Straightness of Sides - ISO 10545-2	± 0,1%	
Regularity of Thickness - ISO 10545-2	± 5%	Surface Quality - ISO 10545-2	Compliant	
Resistance To Staining - ISO 10545-14	Cl. 4	Resistance to Swimming Pool Salts - ISO 10545-13	GA	
Surface Flatness - ISO 10545-2	± 0,35%	Thermal Shock Resistance - ISO 10545-9	Resistant	
Water Absorption - ISO 10545-3	Average Value 0,08% TECHNICAL DATA			
FEATURES & STANDARD	SPECIFICATION			

DCOF - ANSI A.137.1

> 0,42 wet