

RENAISSANCE 24" X 24" CALACATTA GOLD (M) Porcelain



PART NUMBER	PROFILE	AVAILABILITY
PO2314-2424M0	TILE	IN STOCK
GROUT JOINT	DIMENSIONS	ORIGIN
1/16"	23.64" x 23.64" = 3.875 sqft	Italy
NOTES		
Available nationwide.		
Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.		

APPLICATION AREA

WALL	FLOOR	TRAFFIC	EXTERIOR	STEAM SHOWER	WET AREA	POOL
Yes	Residential Floor Use Only	Heavy Commercial	Yes	Wall Only	Wall Only	Yes
BACKSPLASH	FIREPLACE SURROUND	INTERIOR				
Yes	Yes	Yes				

The performance of surface covering products often depends on installation, environmental, and usage factors unique to each project. AKDO is not responsible for any effects that may be caused to products due to installation, wear from use, or exposure to environmental factors including but not limited to: hard water, chemicals, heat, flame, smoke, dirt or other substances. It is your responsibility to assess the project to determine if the product you are selecting is appropriate considering the unique characteristics of your installation, and to apply appropriate, high quality sealers when necessary. Please consult your installer for more information.

TECHNICAL DATA

FEATURES & STANDARD	SPECIFICATION	FEATURES & STANDARD	SPECIFICATION
Abrasion Resistance - ISO 10545-6	Compliant	Breaking Strength - ISO 10545-4	Compliant
Coefficient of Thermal Linear Expansion - ISO 10545-8	2 7 10-6 ºC-1	Frost Resistance - ISO 10545-12	Compliant
Coefficient of Restitution - ISO-10545-5	Compliant	Bending Resistance - ISO 10545-4	Compliant
Moisture Expansion - ISO 10545-10	2 0.01% (0.1 mm/m)	Reaction to Fire - EN 13501-1	A1fl
Regularity of Length & Width - ISO 10545-2	Compliant	Regularity of Rectangularity - ISO 10545-2	Compliant
Regularity of Straightness of Sides - ISO 10545-2	Compliant	Resistance to Household Chemicals - ISO 10545-13	A
Resistance to Swimming Pool Salts - ISO 10545-13	A	Booted Ramp Test - DIN 51130	R10
Surface Flatness - ISO 10545-2	Compliant	Water Absorption - ISO 10545-3	0.2%
FEATURES & STANDARD	SPECIFICATION		
DCOF - ANSI A.137.1	> 0.42 Wet		