

FIKA 31 1/2" X 31 1/2" PARQUET CLIFF (M) *Porcelain*



PART NUMBER
PO2607-3232M0

PROFILE
TILE

AVAILABILITY
IN STOCK

GROUT JOINT
1/16"

DIMENSIONS
31.5" x 31.5" = 6.891 sqft

THICKNESS
3/8"

ORIGIN
Italy

NOTES

Available nationwide.

Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

APPLICATION AREA

| WALL | FLOOR | TRAFFIC | EXTERIOR | STEAM SHOWER | WET AREA | POOL | BACKSPASH | FIREPLACE SURROUND |
|------|-------|------------------|----------|--------------|----------|------|-----------|--------------------|
| Yes | Yes | Heavy Commercial | Yes | Yes | Yes | Yes | Yes | Yes |

INTERIOR

Yes

The performance of surface covering products often depends on installation, environmental, and usage factors unique to each project. AKDO is not responsible for any effects that may be caused to products due to installation, wear from use, or exposure to environmental factors including but not limited to: hard water, chemicals, heat, flame, smoke, dirt or other substances. It is your responsibility to assess the project to determine if the product you are selecting is appropriate considering the unique characteristics of your installation, and to apply appropriate, high quality sealers when necessary. Please consult your installer for more information.

TECHNICAL DATA

| FEATURES & STANDARD | SPECIFICATION | FEATURES & STANDARD | SPECIFICATION |
|--|------------------------------------|---|---------------|
| Abrasion Resistance - ISO 10545-6 | Average value 140 | Barefoot Ramp Test - DIN 51097 | Cl. A |
| Breaking Strength - ISO 10545-4 | Average value 3200 N | Frost Resistance - ISO 10545-12 | Resistant |
| Bending Resistance - ISO 10545-4 | Average value 50 N/mm ² | Regularity of Length & Width - ISO 10545-2 | ±0.15% |
| Regularity of Rectangularity - ISO 10545-2 | ±0.2% | Regularity of Straightness of Sides - ISO 10545-2 | ±0.1% |
| Regularity of Thickness - ISO 10545-2 | ±5% | Surface Quality - ISO 10545-2 | Compliant |
| Resistance to Household Chemicals - ISO 10545-13 | UA | Resistance To Staining - ISO 10545-14 | Cl. 4 |
| Resistance to Swimming Pool Salts - ISO 10545-13 | UA | Slip Resistance (Ramp Test) - DIN 51130 | R9 |
| Surface Flatness - ISO 10545-2 | ±0.35% | Thermal Shock Resistance - ISO 10545-9 | Resistant |
| Water Absorption - ISO 10545-3 | Average value 0.08% | | |

TECHNICAL DATA

FEATURES & STANDARD

DCOF - ANSI A.137.1

SPECIFICATION

>0.42 wet

LEED

| MR | MR | MR |
|------------------|--------------------|---|
| Recycled Content | Regional Materials | Sustainability Report |
| 13.7% | 32% | Available self-declared Corporate Sustainability Report (CSR) |

Available Health Product Declaration (HPD) in compliance with the Health Product Declaration open Standard

No VOCs emission

