

FIKA 31 ½" X 31 ½" PARQUET CABIN (M) Porcelain



PART NUMBER PO2608-3232M0

GROUT JOINT 1/16"

ORIGIN Italy

NOTES

Available nationwide.

Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

PROFILE

DIMENSIONS

 $31.5'' \times 31.5'' = 6.891$ sqft

TILE

AVAILABILITY

IN STOCK

THICKNESS

3/8"

APPLICATION AREA

WALL	FLOOR	TRAFFIC	EXTERIOR	STEAM SHOWER	WET AREA	POOL	BACKSPLASH	FIREPLACE SURROUND
Yes	Yes	Heavy Commercial	Yes	Yes	Yes	Yes	Yes	Yes

INTERIOR

Yes

The performance of surface covering products often depends on installation, environmental, and usage factors unique to each project. AKDO is not responsible for any effects that may be caused to products due to installation, wear from use, or exposure to environmental factors including but not limited to: hard water, chemicals, heat, flame, smoke, dirt or other substances. It is your responsibility to assess the project to determine if the product you are selecting is appropriate considering the unique characteristics of your installation, and to apply appropriate, high quality sealers when necessary. Please consult your installer for more information.

TECHNICAL DATA

FEATURES & STANDARD	SPECIFICATION				
Water Absorption - ISO 10545-3	Average value 0.08% TECHNICAL DATA				
Surface Flatness - ISO 10545-2	±0.35%	Thermal Shock Resistance - ISO 10545-9	Resistant		
Resistance to Swimming Pool Salts - ISO 10545-13	UA	Slip Resistance (Ramp Test) - DIN 51130	RIO		
Resistance to Household Chemicals - ISO 10545-13	UA	Resistance To Staining - ISO 10545-14	Cl. 4		
Regularity of Thickness - ISO 10545-2	±5%	Surface Quality - ISO 10545-2	Compliant		
Regularity of Rectangularity - ISO 10545-2	±0.2%	Regularity of Straightness of Sides - ISO 10545-2	±0.1%		
Bending Resistance - ISO 10545-4	Average value 50 N/mm2	Regularity of Length & Width - ISO 10545-2	±0.15%		
Breaking Strength - ISO 10545-4	Average value 3200 N	Frost Resistance - ISO 10545-12	Resistant		
Abrasion Resistance - ISO 10545-6	Average value 140	Barefoot Ramp Test - DIN 51097	Cl. A		
FEATURES & STANDARD	SPECIFICATION	FEATURES & STANDARD	SPECIFICATION		

FEATURES & STANDARD

DCOF - ANSI A. 137.1 >0.42 wet

LEED

MR	MR	MR
Recycled Content	Regional Materials	Sustainability Report
1 0 70/	2.0%	Available self-declared Cornerate Sustainability Penert ICSPI

Declaration (EPD) conform to ISO14025

Material Ingredients

Available Health Product Declaration (HPD) in compliance with the Health Product Declaration open Standard

Low Emitting Materials

Heat Island Effect

 $Light\ color\ SRI > 29$

Energy Performance

akdo.com