

NUVOLA CALACATTA GOLD (P) SLAB *Porcelain*



PART NUMBER
PO2628-SL12P0

PROFILE
SLAB

AVAILABILITY
IN STOCK

DIMENSIONS
62.99" x 125.98" = 55.117 sqft

THICKNESS
12mm

ORIGIN
Italy

NOTES

Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

APPLICATION AREA

| WALL | FLOOR | TRAFFIC | EXTERIOR | STEAM SHOWER | WET AREA | POOL | BACKSPLASH |
|--------------------|----------|-------------|----------|--------------|-----------|------|------------|
| Yes | Yes | Residential | Yes | Wall Only | Wall Only | Yes | Yes |
| FIREPLACE SURROUND | INTERIOR | | | | | | |
| Yes | Yes | | | | | | |

The performance of surface covering products often depends on installation, environmental, and usage factors unique to each project. AKDO is not responsible for any effects that may be caused to products due to installation, wear from use, or exposure to environmental factors including but not limited to: hard water, chemicals, heat, flame, smoke, dirt or other substances. It is your responsibility to assess the project to determine if the product you are selecting is appropriate considering the unique characteristics of your installation, and to apply appropriate, high quality sealers when necessary. Please consult your installer for more information.

TECHNICAL DATA

| FEATURES & STANDARD | SPECIFICATION | FEATURES & STANDARD | SPECIFICATION |
|--|---------------|---|--------------------------------|
| Chemical Resistance - ISO 10545-13 | Resistant | Coefficient of Thermal Linear Expansion - ISO 10545-8 | $\alpha 7.00 \text{ MK} [- 1]$ |
| Frost Resistance - ISO 10545-12 | Resistant | Regularity of Length & Width - ISO 10545-2 | +/- 0.6% |
| Regularity of Rectangularity - ISO 10545-2 | +/- 0.6% | Regularity of Straightness of Sides - ISO 10545-2 | +/- 0.5% |
| Regularity of Thickness - ISO 10545-2 | +/- 5% | Resistance To Staining - ISO 10545-14 | Cl. 3 |
| Surface Flatness - ISO 10545-2 | +/- 0.5% | Thermal Shock Resistance - ISO 10545-9 | Resistant |
| Water Absorption - ISO 10545-3 | $\leq 0.5\%$ | DCOF – ANSI A326.3:2019 | > 0.42 Wet |